


## Dyform 50DB

- Crush resistant
- Reduced sheave wear
- Good wear characteristics
- Excellent spooling
- Rotation resistant



Nominal rope Diameter	Nominal rope length mass In air	Min Breaking Force (F min)		Nominal metallic cross section
		EIPS / 1960 grade		
mm	Kg/m	kN	tonnes	mm <sup>2</sup>
8	30.2	57.2	5.83	36.1
9	38.2	72.4	7.38	45.7
10	47.2	89.3	9.11	56.4
11	57.1	108	11.0	68.3
12	68.0	129	13.1	81.2
13	79.8	151	15.4	96.3
14	92.5	175	17.9	111
15	106	201	20.5	127
16	121	229	23.3	144
17	136	258	26.3	163
18	153	289	29.5	183
19	170	323	32.9	204
20	189	357	36.4	226
21	208	394	40.2	249
22	228	432	44.1	273
23	250	473	48.2	298
24	272	515	52.5	325
25	295	568	56.9	353
26	319	604	61.6	381